

ES 65 S

1.2363 soft-annealed
X 100 CrMoV 5

Also available in EST grade.

Characteristic or application:

air hardening special cold work tool steel for cutting and pressing tools, moulds for plastics processing, rollers, shearing knives, thread rolling dies, cold stamping tools and measuring tools

Thickness in mm	40	50	60	70	80	100	120	150	200
	1010	1010	1010	1010	1010	600	600	600	400

ES 265 W

1.2367 soft-annealed
X 38 CrMoV 5-3

Also available in EST grade.

Characteristic or application:

hot work tool steel for heavy metal, extrusion and pressure die casting tools with high toughness, very good high temperature strength and hardness retention

Diameter in mm	Availability: Ø 25mm black, from Ø 30mm peeled or machined										
	25	46	62	92	121	152	182	212	252	303	363
	30	52	72	101	131	162	196	222	262	323	
	42	56	77	111	142	172	202	232	282	333	

18

ES 265 W ESR

1.2367 ESR soft-annealed
X 38 CrMoV 5-3

Characteristic or application:

hot work tool steel for heavy metal, extrusion and pressure die casting tools with the highest toughness requirements

Thickness in mm	225	300
	600	600

Other sizes can be supplied at short notice.

