

ES Multiform SL

Special alloy

Tensile strength:

280-325 HB (950 – 1100 N/mm²)

Characteristic or application:

All-purpose tool steel ideally suited for graining, structurally erodible with good polishing and welding properties. It can be nitrated and chromium-plated; and features uniform hardness throughout the cross-section to a thickness of 600 mm.

Diameter in mm	Availability: peeled or machined																				
	20,5	26	31	41	51	61	71	81	91	101	111	121	131	141	151	161	172	182	202	212	
	222	232	252	272	282	303	323	353	383	403	423	453	483	503	523	553	603				

Thickness in mm	25	30	35	40	50	60	70	80	90	100	110	120	130	150	175	205	225	255	275
	1250	1250	1250	1250	1250	1250	1250	1250	1250	1250	1250	1250	1250	1250	1250	1600	1600	1600	1600

Thickness in mm	305	325	355	375	405	425	455	475	505	555	600
	1600	1600	1600	1600	1250	1250	1250	1600	1250	1250	1250
					1600	1600	1600		1600	1600	1550

